

ADVANTEC 過濾膜耐藥品性表

溶劑名稱		過 濾 膜 材 質			
		A	C	J	H
酸	冰醋酸	x	x	●	●
	10% 乙酸	●	●	●	●
	12N 37%硫酸亞鐵	x	x	●	●
	6N 19% 硫酸亞鐵	◆	x	●	●
	12N 53% 硝酸	x	x	●	◆
	6N 26% 硝酸	◆	x	●	●
	36N 96% 硫酸	x	x	●	x
	6N 16% 硫酸	◆	x	●	●
	85% 磷酸	●	x	●	●
	5% 硼酸	●	●	●	●
類	50% 甲酸	◆	◆	●	●
	35% 氫氟酸	x	x	●	●
	60% 高氯酸	●	x	●	●
	氫氧化鉀、苛性鉀	x	x	●	●
	苛性鈉、氫氧化鈉	x	x	●	●
鹼類	氫氧化鉍	x	x	●	●
醇	甲醇	x	●	●	●
	乙醇、酒精	x	●	●	●
	異丙醇、丙醇	◆	●	●	●
	異丙醇	◆	●	●	●
	丁醇	●	●	●	●
	甘油	●	●	●	●
	戊醇	◆	●	●	●
	苯甲醇	◆	x	●	●
	乙醇	x	●	●	●
醚類	二乙醚	◆	●	◆	●
	二異丙醚	●	●	●	●
	二氧陸圀	x	x	●	●
	石油腦	●	●	●	●
脂類	甲脂	x	x	●	●
	丁脂	x	x	●	●
	戊脂	x	◆	●	●
酮類	丙酮	x	◆	●	●
	甲丙酮	x	x	●	●
	異丁乙酮	x	x	●	●
	環己烷	x	x	●	●

● 適合使用 ◆ 特定條件下可使用 x 不適合使用

ADVANTEC 過濾膜耐藥品性表

溶劑名稱		過 濾 膜 材 質			
		A	C	J	H
碳 氫 化 合 物	苯	●	●	●	●
	甲苯	●	●	●	●
	二甲苯	●	●	●	●
	已醇	●	●	●	●
	汽油	●	●	◆	●
	煤油	●	●	●	●
鹵 碳 化 合 物	氯仿	●	x	◆	●
	中二氯代甲	x	x	◆	●
	三氯乙烯	●	●	●	●
	中四氯代乙烯	●	●	●	●
	四氯化碳	●	●	◆	●
氨 類	苯胺	x	x	●	●
	二甲基甲	x	x	●	●
	三乙基乙醯胺	x	x	●	●
	三乙醇安	x	●	●	●
	乙二醇-甲醚	x	x	●	●
	乙二醇-丁醚	x	●	●	●
氣 體 類	氮氣	●	●	●	●
	氫氣	●	●	●	●
	氧氣	●	●	●	●
	過氧化氫	x	●	●	●
	鹽水	●	●	●	●
	二甲亞碲	x	x	●	●
其 他	硝基苯	x	x	●	●
	甲醇、氯仿	◆	x	●	●
	四氫化呋喃	x	x	x	●
	吡啶	x	x	●	●
	乙睛	x	x	●	●
	酚	●	x	●	●
	三氯氮代甲烷	●	●	●	●
	甲醛	◆	◆	●	●
	矽油	●		●	●
	95% 已烷	x	●	●	●
	酯				●
	70% 乙睛:30% 水	x	x	●	●
	石油	●	●	●	●

● 適合使用 ◆ 特定條件下可使用 x 不適合使用